

Epoxy Intumescent

PRODUCT DESCRIPTION

Chartek ONE is a high performance, boron free, modified epoxy intumescent fire protection solution, based on patented technology.

The product is a high build, self-reinforced, two pack material providing excellent durability and combined corrosion and fire protection.

Chartek ONE is suitable for application to carbon and galvanised steel. Tested in accordance with ANSI UL1709, BS476-20/21 (Part 20 Appendix D), EN1363-2, ISO TR834-3:1994, ISO 20902-1, IMO Resolution MSC.307(88): 2010 (hydrocarbon time temperature furnace heating curve), ISO 22899-1, ISO 22899-3 (Draft), UL2431, ISO 12944-9 and Norsok M501:2022 Rev. 7, systems 5A and 5S.

INTENDED USES

Suitable for the protection of steel from the effects of hydrocarbon pool and jet fires (100-350kW/m²) and may be applied as one coat without material or metal reinforcement.

To preserve the functional integrity of structures and process equipment for a specified period of time.

Primarily intended for use in high risk environments such as oil, gas, LNG, petrochemical and power generation industries.

PRACTICAL INFORMATION FOR CHARTEK ONE

Gloss Level Not applicable

Volume Solids 100%

Typical Thickness Depends on protection required.

Theoretical Coverage 1kg of Chartek ONE will provide 1mm of fire protection to 0.87m² (based on plural component application).

Practical Coverage Allow appropriate loss factors

Density 1150 kg/m³ (71.8 lb/ft³) plural spray applied (ISO 1183-1 (2019))

Method of Application Heated Plural Component Airless Spray

Drying Time

Temperature	Touch Dry	Hard Dry	Overcoating interval with self	
			Minimum	Maximum
10°C (50°F)	6 hours	22 hours	2 hours	*
25°C (77°F)	3 hours	12 hours	2 hours	*
40°C (104°F)	2 hours	6 hours	60 minutes	*

*Please consult AkzoNobel for further information.

REGULATORY DATA

Flash Point (Typical) Part A >100°C (212°F); Part B >100°C (212°F); Mixed >100°C (212°F)

VOC 3 g/kg EU Solvent Emissions Directive (Council Directive 2010/75/EU)

Coating hazard marker GB 30981.2-S-Pb≤1000-NC Qualified for GB 30981.2-2025

See Product Characteristics section for further details

Protective Coatings

Epoxy Intumescent

SURFACE PREPARATION

Surface preparation and application should be carried out in accordance with the advice given in AkzoNobel Chartek ONE Application Manual.

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2019.

Abrasive Blast Cleaning

Chartek ONE is typically applied to surfaces which have been abrasive blast cleaned to a standard of Sa2½ (ISO8501-1:2007) or SSPC-SP10 and suitably primed.

Primers

Selected primers or priming systems must be stated on the qualified primer list from AkzoNobel. The preferred primer shall be an epoxy type at a specified thickness not exceeding 75 microns (3 mils). Alternatively, a two coat primer system, such as epoxy zinc and tie coat may be used; the combined specified thickness should not exceed 110 microns (4.5 mils).

APPLICATION

Mixing	For trowel application individual components should be stored at 35°C (95°F) and fully power agitated before mixing.	
Mix Ratio	1.31 part(s): 1 part(s) by weight (Refer to the Chartek ONE Application Manual)	
Working Pot Life	10°C (50°F) 30 minutes	25°C (77°F) 30 minutes
	40°C (104°F) 20 minutes	
	Pot life values refer to trowel workability without thinning, heated to 35°C (95°F) before mixing. If material is not pre-heated pot life will be extended but mixing will be more difficult. Working pot life is not applicable for plural airless spray application as the product is only mixed at the static mixer close to the spray gun, at the point of application. Refer to the Chartek ONE Application Manual.	
Plural Component Airless Spray	Recommended and preferred	Refer to the Chartek ONE Application Manual
Airless Spray	Recommended	Refer to the Chartek ONE Application Manual
Trowel Thinner	Suitable Not normally required	Refer to the Chartek ONE Application Manual Only for pre-mix - consult Chartek ONE Application Manual
Cleaner	International GTA822	
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA123. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.	
Clean Up	Clean all equipment immediately after use with International GTA822. It is good working practice to periodically clean equipment during the course of the working day. Frequency of cleaning will depend upon amount used, temperature and elapsed time, including any delays.	
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.	

Epoxy Intumescent

PRODUCT CHARACTERISTICS

The following conditions shall apply (or be generated) throughout the application:

Minimum Air Temperature	-10°C (14°F)
Maximum Humidity	85%
Surface Temperature	A minimum of 3°C (5°F) above dew point of surrounding air.
General	Surfaces must be clean, dry and free from contaminants immediately prior to coating.

Application

Chartek ONE should be spray applied to ensure total wetting of the substrate is achieved. Where this is not possible by spray alone, then the first coat should be thoroughly trowelled and rolled to achieve this. The best time to overcoat Chartek ONE with itself is as soon after the minimum overcoating interval has been achieved or before the coating has had any chance to become contaminated. Where Chartek ONE is overcoated with cosmetic topcoats, the following overcoat intervals will apply:

	Minimum	Maximum
10°C (50°F)	24 hours	14 days
25°C (77°F)	24 hours	14 days
40°C (104°F)	24 hours	14 days

Mesh

As standard, all fire types and fire rating do not require any reinforcement mesh. If this is required for specific circumstances, seek advice from AkzoNobel.

Equipment

As detailed in the Chartek ONE Application Manual.

Applicator Qualification

Only companies in receipt of Qualified Applicator status from AkzoNobel shall be used for Chartek ONE application. Companies shall document that they comply with this requirement prior to work commencement. The Chartek ONE application shall be conducted by the Applicator Company using employees trained and qualified in the proper application procedures. As a minimum, Supervisory and QA/QC personnel on site shall be in receipt of individual qualifications, having attended an AkzoNobel Chartek Applicator Training School. This is a minimum requirement and shall be documented prior to work commencement.

Inspection & QA

This is the responsibility of the Applicator but as a minimum must conform to the procedures laid down in AkzoNobel Chartek QC Manual.

Technical Service

This is available from AkzoNobel and should be co-ordinated to ensure attendance at job start up. The Applicator Company is responsible for ensuring AkzoNobel is notified of start up date.

Alternative Surface Preparation

Under certain project specific circumstances, AkzoNobel has developed procedures for wet blasting, ultra high pressure water blasting (hydroblasting) and power tool cleaning.

Maximum Surface Operating Temperature

At service temperatures of between 100°-120°C (212°-248°F) a suitable thermal barrier, e.g. Intertherm 7050, should be used between the substrate and the Chartek ONE.

Note: applied density values are typical and are provided for guidance purpose only. Please refer to the Chartek ONE Application Manual.

SYSTEMS COMPATIBILITY

Chartek ONE is designed for application to correctly prepared substrates which have been suitably primed. The following primer examples are qualified for use with Chartek ONE:

Interdur 8817	Intergard 7500
Intershield 300	Intershield 300HS
Interzinc 52E/Intergard 269	

Generally Chartek ONE will be topcoated to meet owners' colour schemes and finish requirements. AkzoNobel recommends the use of topcoats in all external applications. The following topcoats are recommended for Chartek ONE:

Interthane 990	Interfine 878
----------------	---------------

For more information regarding approved primers and topcoats, please contact International Protective Coatings

Epoxy Intumescent

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Safety Data Sheet and the container(s), and should not be used without reference to the Safety Data Sheet (SDS).

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult AkzoNobel for further advice.

PACK SIZE

Kit Size	Part A Weight	Part B Weight
40kg (88.2lb) kit	22.7kg (50.1lb)	17.3kg (38.1lb)

SHIPPING WEIGHT (TYPICAL)

Kit Size	Part A Weight	Part B Weight
40kg (88.2lb) kit	24.9kg (54.9lb)	19.5kg (43lb)

STORAGE

Shelf Life	12 months minimum. Should be stored in conditions from 1°C (34°F) to 30°C (86°F), indoors and out of direct sunlight.
------------	---

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 29/06/2026.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

www.international-pc.com